

## Post Consumer Mailer (PCM) eCommerce Mailer Film

## TECHNICAL DATA SHEET

Specifically engineered for ecommerce order fulfillment applications.

Press Printing	Yes with restrictions
Imprinting	Yes
Trim Seal	Yes
Configurations	Autobag®; SidePouch® with restrictions

	ASTM Test Method	Thickness (mi 2.0 2.5
Haze (%)	D-1003	Opaque Opaq
Puncture Resistant - Dart (g)	D-1709	255 259
Tensile Strength (@ Break MD)	D-882A	16 15
Tensile Strength (@ Break TD)	D-882A	15 15
Elongation (@ Break MD)	D-882A	594 593
Elongation (@ Break TD)	D-882A	702 752
Elmendorf Tear MD (g)	D-1922	443 571
Elmendorf Tear TD (g)	D-1922	1432 1761

 $\mathsf{MD} = \mathsf{Longitudinal\ Direction} \ / \ \mathsf{TD} = \mathsf{Transverse\ Direction}$ 

This information represents our best judgment based on the work done. The company assumes no liability whatsoever in connection with the use of information or findings contained herein. Current data is based on limited samples and is subject to modification pending finalization.

www.sealedair.com 🛒